



COTTON AND POLYESTER

POLYURETHANE	70-80µm	Flex blade 45°	Medium to high Pressure	Standard	Low Temperature	Quick application on to Cotton, Polyester, Poly-Cotton	HOT or COLD Peel
				120°C	110-115°C	140°C	
				20s	25-30s	5/7s	

NYLON

POLYURETHANE	70-80µm	Flex blade 45°	Medium to high Pressure	Standard			HOT or COLD Peel
				140°C			
				20-25s			

SPECIFICATIONS

APPLICATION

- Cut the material in reverse with a Flex regular blade.
- Weed the excess material.
- Heat press using a SEFA machine on the garment following instructions (time and temperature) & Protect the polyester carrier with silicone paper.
- Peel the carrier off when cold or hot.

THICKNESS: 70-80 microns

CARRIER: Adhesive & Transparent polyester

CERTIFICATES: Oeko-Tex Label Standard 100 Class I



APPLIES ON

Cotton ● Polyester ● Acrylic ● Similar Fibres ● Nylon

CARE & MAINTENANCE

- Always respect the garment's instructions
- Allow 24 hours after application before washing
- Iron the backside only

WASH

- Max 60°C : Cotton & Polyester
Max 40°C : Nylon
- Preferably inside out
- Do not bleach
- Tumble-dry approved
- Dry-cleaning approved

STORE

- Up to 1 year
- In a dry room (15-30° C)
- Away from sunlight
- In vertical position



NOTE: For best results, it is recommended to TEST prior to starting standard production